

Interlam™

Pro Matte

Interlam™ Pro Matte is a 75µ (3 mil) monomeric soft calendared PVC laminating film with a matte finish, coated on one side with a pressure sensitive, aqueous acrylic adhesive that is protected by a bleached Kraft release paper coated on one side with PE and siliconised on the release side.

- RECOMMENDED FOR INTERIOR AND EXTERIOR USE WHERE A NON-GLARE FINISH IS REQUIRED OR WHERE SPECIFIC LIGHTING CONDITIONS CANNOT BE CONTROLLED
- IDEAL FOR POP DISPLAYS, ARCHITECTURAL RENDERINGS, PROMOTIONAL DISPLAYS, EVENT SIGNAGE AND PHOTOGRAPHIC IMAGES
- INTERLAM™ PRO MATTE HAS A CLASS 0 FIRE RATING ACCORDING TO UK STANDARDS FOR SURFACE SPREAD OF FLAME, MAKING IT PERFECT FOR APPLICATIONS IN PUBLIC AREAS THAT REQUIRE COMPLIANCE WITH STRICT FIRE REGULATIONS, SUCH AS AIRPORTS, HOTELS AND HOSPITALS

For more information, performance and warranty guide lines please contact your local Drytac office.

© 2019 Drytac Corporation. E&OE. All other trademarks are the property of their respective owners.

TECHNICAL SPECIFICATION

PRODUCT STRUCTURE

Film	Matte Monomeric Soft Calendared PVC
Adhesive	Acrylic (Pressure Sensitive)
Release Liner	1 Side PE Coated

PRODUCT CHARACTERISTICS

Film Thickness	3 mil (75µ) 4 mil
Adhesive Layer	1 mil (25µ) (100µ)
UV Protection Factor	Film contains UV stabilizers, which prevent film degradation and provide UV protection to the underlying image
Outdoor Durability	5 Years (Ink Dependent)
Fire Rating	Class 0
Application Temperature	>41°F (20°C)
Service Temperature Range	-13°F to 302°F (-25°C to 150°C)
Peel Strength (20 min, FTM1)	11 N/25mm
Shelf Life	1 year
Storage Conditions	59°F to 72°F (15°C to 22°C); 50 - 55% Relative Humidity

PROCESS SETTINGS

Equipment Type & Temperature	Speed
Roller Laminator Room temperature to 104°F (40°C)	1 ft to 8 ft (0.3m to 2.5m) per minute
Press	Not recommended

DRYTAC®
ADHESIVE SCIENCE

www.drytac.ch

hello@drytac.ch

talicq
IMAGING

Tel. 041 525 34 34

Talicq SA
Rengglochstrasse 34
6012 Obernau
info@talicq.com
www.talicq.com

www.drytac.ch